



EDUARD MERKLE GMBH & CO. KG

KALK-, TERRAZZO-UND STEINMAHLWERKE D-89143 Blaubeuren-Altental Tel. +49(0) 73 44-96 01-0 Fax +49(0) 73 44-96 01-11

JURAPERLE KM

Chemical analysis of JURAPERLE

CaCO ₃	(DIN EN 15309)	97,5 %
MgCO ₃	(DIN EN 15309)	0,4 %
Fe ₂ O ₃	(DIN EN 15309)	0,1 %
Al ₂ O ₃	(DIN EN 15309)	0,2 %
SiO ₂ (Silicates)	(DIN EN 15309)	0,8 %
Volatile matter (105°C)	(DIN EN ISO 787-2)	< 0,2 %
Loss on ignition	(DIN EN 459-2)	42,9 %
HCl-insoluble	(DIN 55 918)	1,2 %

Physical data

		g/cm ³
Loose bulk density		0,8 g/cm ³
Packed bulk density	(DIN EN ISO 787-11)	1,4 g/100g
Oil absorption	(DIN EN ISO 787-5)	15 g/100g
DOP absorption	(DIN EN ISO 787-5)	24 µS/cm
Electrical conductivity (10%)	(DIN EN ISO 787-14)	47
pH value	(DIN EN ISO 787-9)	9,6 g/cm ³
Density	(DIN EN ISO 787-10)	2,7
Refractive index		1,6
Hardness (Mohs)		3

Optical properties

Brightness	(C/2°, DIN 53163)	84,7
Yellow-index	(DIN 6167)	14,3
CIELAB-Colour values	(DIN 6174)	L* 95,3
		a* 0,5
		b* 7,4

The above data are average values from numerous measurements, published without legal commitment.

Sieve analysis (DIN 53 734)

Percentage of particles finer than	90 μm	99,9 %
	40 μm	95,5 %

Particle size distribution (Laser-Granulometer)

Percentage of particles finer than	24 μm	90 %
	16 μm	80 %
	8 μm	65 %
	4 μm	44 %
	2 μm	25 %

Mean particle size: 4,4 μm

Particle size distribution curve of JURAPERLE KM (Laser-Granulometer Sympatec Helos R3, Air jet sieve)

