



EDUARD MERKLE GMBH & CO. KG

KALK-, TERRAZZO- UND STEINMAHLWERKE 89143 Blaubeuren-Altental Tel. (073 44) 96 01-0 Fax (073 44) 96 01-11

ULMER WEISS WL**Chemical analysis of ULMER WEISS**

CaCO ₃	99,2 %	
MgCO ₃	0,4 %	
Fe ₂ O ₃	0,035 %	
Al ₂ O ₃	0,1 %	
SiO ₂ (Silicates)	0,25 %	
Volatile matter (105°C)	(DIN EN ISO 787-2)	< 0,2 %
Loss on ignition	(DIN EN 459-2)	43,8 %
HCl-insoluble	(DIN 55 918)	0,3 %

Physical data

Loose bulk density		0,75 g/cm ³
Packed bulk density	(DIN EN ISO 787-11)	1,4 g/cm ³
Oil absorption	(DIN EN ISO 787-5)	16 g/100g
DOP absorption	(DIN EN ISO 787-5)	27 g/100g
Electrical conductivity (10%)	(DIN ISO 787-14)	46 μS/cm
pH value	(DIN EN ISO 787-9)	9,6
Density	(DIN EN ISO 787-10)	2,7 g/cm ³
Hardness (Mohs)		3
Refractive index		1,59

Optical properties

Brightness	(C/2 ⁰ , DIN 53163)	88
Yellow-index	(DIN 6167)	5,2
CIELAB-Colour values	(DIN 6174)	L* 95 a* 0,2 b* 2,9

optical brightener: Ultramarin

The above data are average values from numerous measurements, published without legal commitment.

Sieve analysis (DIN 53 734)

Percentage of particles finer than 40 µm 99,9 %

Particle size distribution (Laser-Granulometer)

Percentage of particles finer than	24 µm	98,1 %
	16 µm	91 %
	8 µm	72 %
	4 µm	46 %
	2 µm	25 %

Mean particle size: 5,0 µm

**Particle size distribution curve of ULMER WEISS WL
(Laser-Granulometer Sympatec Helos R3)**

