



EDUARD MERKLE GMBH & CO. KG

KALK-, TERRAZZO- UND STEINMAHLWERKE D-89143 Blaubeuren-Altental Tel. +49(0)7344-9601-0 Fax +49(0)7344-9601-11

ULMER WEISS XMF**Chemical analysis of ULMER WEISS**

CaCO ₃	99,2 %	
MgCO ₃	0,4 %	
Fe ₂ O ₃	0,035 %	
Al ₂ O ₃	0,1 %	
SiO ₂ (Silicates)	0,25 %	
Volatile matter (105°C)	(DIN EN ISO 787-2)	< 0,2 %
Loss on ignition	(DIN EN 459-2)	43,8 %
HCl-insoluble	(DIN 55 918)	0,3 %

Physical Data

Loose bulk density		0,61 g/cm ³
Packed bulk density	(DIN EN ISO 787-11)	1,15 g/cm ³
Oil absorption	(DIN EN ISO 787-5)	18 g/100g
DOP absorption	(DIN EN ISO 787-5)	34 g/100g
Electrical conductivity (10%)	(DIN ISO 787-14)	71 μS/cm
pH value	(DIN EN ISO 787-9)	9,6
Density	(DIN EN ISO 787-10)	2,7 g/cm ³
Hardness (Mohs)		3
Refractive index		1,59

Optical properties

Brightness	(C/2°, DIN 53163)	92,5
Yellow-index	(DIN 6167)	7
CIELAB-Colour values	(DIN 6174)	L* 97,0
		a* -0,2
		b* 3,9

The above data are average values from numerous measurements, published without legal commitment.

Sieve analysis (DIN 53734)

Percentage of particles finer than 40 µm >99,9 %

Particle size distribution (Laser-Granulometer)

Percentage of particles finer than

12 µm	99,2 %
8 µm	94 %
4 µm	65 %
2 µm	34 %

Mean particle size: 3,0 µm

**Particle size distribution curve of ULMER WEISS XMF
(Laser-Granulometer Sympatec Helos R3)**

